

KUMHO KTR[®] 401H

Technical Data Sheet

| Product Description |

KUMHO KTR[®] 401H polymer is a radial block copolymer based on styrene and butadiene with bound styrene of 32.5% mass. It is supplied in two physical forms, identified as follows in the grade nomenclature:

- KTR 401H supplied as porous pellets
- KTR 401HP supplied as powder

| Typical Properties |

Property	Value
Molecular structure	Radial (S-B) X 4
Physical form	Porous pellet / Powder
Styrene content (wt%)	32.5
Volatile matter (wt%)	0.5
Ash content (wt%)	0.08
Solution viscosity at 25°C (cps) - 5.23wt% in toluene	21.5
Tensile strength (kg _f /cm ²)	280
Elongation (%)	710
Tensile modulus at 300% (kg _f /cm ²)	34
Hardness, shore A / 5 sec (degree)	87
Melt flow index at 200°C, 5kg (g /10min)	max. 1
Specific gravity	0.94
Extended oil content (wt%)	0
Application	Bitumen modifier

* The above data is typical, therefore there may be a slight difference from the physical properties of the supplied product.

| Characteristics |

Fields	Characteristics
Bitumen modifier - road paving - roofing sheets	<ul style="list-style-type: none">• Increase softening point of bitumen• Reduce the sensitivity to temperature change• Improve low temperature flexibility• Improve elasticity and impact resistance• Extend life span of pavement

| Package |

CAS NO	Packing unit (kg)	
	Paper bag (Pallet)	Jumbo bag
9003-55-8	15 (600)	450, 500

| Handling Precaution |

The direct exposure to sunlight, heat, and humidity may cause discoloration or deterioration.

Keep the product away from sunlight, humidity, and chemicals, and store in cool and dry places below 35°C.