

Technical Data Sheet (ASTM)

ABS(Acrylonitrile Butadiene Styrene) HU650

Features	Super heat resistance
Applications	Automobile parts, Mirror housing, Radiator grills, Rear lamp housings

Physical	Test Method	Value
Density	ASTM D792	1.06 g/cm ³
Melt Flow Index (200°C, 21.6kg)	ASTM D1238	6 g/10min
Water absorption	ASTM D570	- %
Mold Shrinkage	ASTM D955	0.5 ~ 0.8 %

Mechanical	Test Method	Value
Tensile Strength	ASTM D638	48 MPa
Elongation	ASTM D638	25 %
Flexural Strength	ASTM D790	69 MPa
Flexural Modulus	ASTM D790	2,270 MPa
Izod Impact Strength(3.2mm, 23°C)	ASTM D256	147 J/m
Izod Impact Strength(6.4mm, 23°C)	ASTM D256	127 J/m
Rockwell Hardness(R scale)	ASTM D785	111

Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	105 °C
Vicat Softening Temperature(5kg, 50°C/h)	ASTM D1525	115 °C

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.