

Technical Data Sheet

**ABS & PC Alloy (Engineering Plastics)
HAC 8250W**

Features Weather Resistant
Applications

Physical	Test Method	Value
Density	ASTM D792	1.13 g/cm ³
Melt Flow Index (230°C, 21.6kg)	ASTM D1238	45 g/10min
Mold Shrinkage	ASTM D955	0.5 ~ 0.7 %
Water absorption	ASTM D570	- %

Mechanical	Test Method	Value
Tensile Strength	ASTM D638	550 kg/cm ²
Elongation	ASTM D638	100 %
Flexural Strength	ASTM D790	750 kg/cm ²
Flexural Modulus	ASTM D790	20,000 kg/cm ²
Izod Impact Strength(6.4mm)	ASTM D256	50 kg-cm/cm
Rockwell Hardness(R scale)	ASTM D785	115

Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	104 °C (219) (°F)
Vicat Softening Temperature(5kg, 50°C/h)	ASTM D1525	°C (°F)

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.