

Technical Data Sheet (ASTM)

**ABS(Acrylonitrile Butadiene Styrene)
ABS 775K**

Features Refrigerator sheet, High impact resistance
Applications Refrigerator inner case, door liner (Cyclepentane foaming agent use)

Physical	Test Method	Value
Density	ASTM D792	1.04 g/cm ³
Melt Flow Index (220°C, 10kg)	ASTM D1238	6 g/10min
Melt Flow Index (200°C, 21.6kg)	ASTM D1238	9 g/10min
Mold Shrinkage	ASTM D955	0.5 ~ 0.8 %
Water absorption	ASTM D570	- %
Mechanical	Test Method	Value
Tensile Strength	ASTM D638	470 kgf/cm ² (6,681) (psi)
Elongation	ASTM D638	25 %
Flexural Strength	ASTM D790	620 kgf/cm ² (8,680) (psi)
Flexural Modulus	ASTM D790	23,000 kgf/cm ² (326,600) (psi)
Izod Impact Strength(3.2mm, 23°C)	ASTM D256	44 kgf-cm/cm (8.1) (ft-lb/in)
Izod Impact Strength(6.4mm, 23°C)	ASTM D256	34 kgf-cm/cm (6.2) (ft-lb/in)
Rockwell Hardness(R scale)	ASTM D785	105
Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	88 °C (190) (°F)
Vicat Softening Temperature(5kg, 50°C/h)	ASTM D1525	98 °C (208) (°F)
Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.